


Data sheet 13 mercury free



Specifications:

Chemical system:	Zinc / Air
Nominal voltage:	1,45 V
Typical Capacity:	300 mAh*
IEC Standard Test Capacity:	280 mAh**
IEC Wireless Test Capacity:	260 mAh***
Impedance:	max. 7,5 Ω@ 1kHz
Weight:	approx 0,83 g
Volume:	approx 0,26 ccm
Storage:	10-30°C / 20-80 % r.h.
Operating:	0-45°C / 25-70 % r.h.
Short Exposition:	-10-65°C / 5-95 % r.h.

*625 Ohms 12h/day to 0.9V at 20°C / 55% r.h.

**IEC Hearing aid standard test to 1,05 V at 20°C / 55% r.h. according to IEC 60086-2:2015/DIN EN 60086-2:2016


***IEC Wireless streaming test to 1,1 V at 20°C / 55% r.h. according to IEC 60086-2:2015/DIN EN 60086-2:2016

Dimensions:

according to IEC 60086-2:2015/DIN EN 60086-2:2016

IEC: PR48

Typical discharge characteristics at 20°C / 55% r.h.:



VARTA Microbattery GmbH
 VARTA – Platz 1
 D 73479 Ellwangen
 Tel.: +49 7961 921 0
 www.varta-microbattery.com

The intended purpose of zinc/air cells is the use as energy source in hearing aids. Thus they are medical devices in the sense of various Medical Device Regulations. Guidelines for safe handling as well as other important safety information can be obtained from our Safety Data Sheet (download from www.powerone-batteries.com). This data is subject to change without prior notice. Performance information is typical. Contact VARTA for latest information. Date of issue: March 2020